

CORNING

Specialty Materials Division

Optical Materials

Product Information

Glass Codes 7978 and 7979



Glass codes 7978 and 7979 are high purity, noncrystalline silica glasses that combine a very low thermal expansion coefficient with excellent optical qualities and exceptional transmittance. Characteristics include homogeneity, low birefringence and outstanding transmittance in the DUV, UV, visible, and infrared ranges.

Different forms and grades of each glass code are available as indicated below.

Quality Grade Selection Chart


	HPFS® 7978 UV	HPFS® 7978 Infrared	7978 Non-UV	HPFS® 7979 UV	HPFS® 7979 Infrared	7979 Non-UV
Maximum Visible Transmittance	■	■	■	■	■	■
Maximum UV Transmittance	■			■		
Maximum Infrared Transmittance					■	
Homogeneity: AA,A,C,F (By Size)	■	■		■	■	
Inclusion Class: 0,1,2,5	■	■		■	■	
Economical (No certification of any properties except visible transmission)			■			■
No Striae in Use-Axis	■	■		■	■	
Homogeneity Certified in Off-Axis: A, C, F (By Size)	■			■		
Minimum Birefringence	■			■		
Minimum Fluorescence	■	■		■	■	
UV Laser Resistance	■			■		

Inclusion Class			Homogeneity ^{3,4,5} ppm				
Class	Total Inclusions ¹ Cross Section [mm ²]	Maximum ² Size [mm]	A	A	C	F	G
			≤0.5	≤1	≤2	≤5	NS
0	≤0.03	0.10	■	■	■	■	■
1	≤0.10	0.28		■	■	■	■
2	≤0.25	0.50			■	■	■
5	≤2.00	1.27			■	■	■


Notes:

1. Defines the sum of the cross section in mm² of inclusions per 100 cm³ of glass. Inclusions with a diameter ≤ 0.10 mm are disregarded.
2. Refers to the diameter of the largest single inclusion.
3. Index homogeneity: the maximum index variation (relative), measured over the clear aperture of the blank.
4. Index homogeneity is certified using an interferometer at 632.8 nm. The numerical homogeneity is reported as the average through the piece thickness. The maximum thickness for index homogeneity verification is 20 mm. For thinner parts, the parent piece is certified.
5. NS (not specified)

185-400nm Internal Transmittance (%/cm)



400-5000nm Internal Transmittance (%/cm)



Refractive Index and Dispersion

Data in 22°C in 760mm Hg dry nitrogen gas

Wavelength [air] λ [nm]	Refractive Index *2 n	Thermal Coefficient Δn/ΔT*3 (ppm/K)	Polynomial Dispersion Equation Constants, 20°C ¹
1813.08	1.440791	9.8	A ₀ 2.104229389E+00
1529.58	1.44352	9.5	A ₁ -1.002155533E-04
1128.64	1.448944	9.8	A ₂ -9121749105E-03
1013.98 n _t	1.450317	9.8	A ₃ 8.782635767E-03
852.11 n _s	1.452538	9.7	A ₄ 8.780464839E-05
780.02	1.453742	9.9	A ₅ 1.307069116E-06
643.85 n _{c'}	1.456775	10.1	A ₆ 5.398453121E-09
546.07 n _e	1.460148	10.3	A ₇ 1.786158843E-10
479.99 n _{F'}	1.463572	10.5	A ₈ 7.514786588E-12
404.66 n _h	1.469686	11.0	Sellmeier Dispersion Equation Constants, 20°C²
340.36	1.478656	11.8	B ₁ 1.589275328E-01
312.57	1.484564	12.3	B ₂ 6.229767186E-01
289.36	1.491067	12.8	B ₃ 3.223549560E-01
253.65	1.505595	14.2	B ₄ 9.122465810E-01
228.80	1.521228	15.7	C ₁ 8.861164451E-04
214.44	1.533799	17.1	C ₂ 6.595885054E-03
206.20	1.542744	18.2	C ₃ 1.401773626E-02
194.17	1.588999	20.3	C ₄ 9.972998819E+01
184.89	1.575106	22.6	Δn/ΔT Dispersion Equation Constants, 20-25°C³
			C ₀ 9.4950
			C ₁ 0.2622
			C ₂ -0.00231
			C ₃ 0.0002944
			Other Optical Properties
			V _e 67.70
			n _F -n _{C'} 0.006797
			Stress Coefficient 35.0 nm/cm MP _a
			Striae ISO 10110-4 Class 5
			Birefringence ≤ 1nm/cm, lower specifications available

1 Polynomial Equation: $n^2 = A_0 + A_1 \lambda^4 + A_2 \lambda^2 + A_3 \lambda^{-2} + A_4 \lambda^{-4} + A_5 \lambda^{-6} + A_6 \lambda^{-8} + A_7 \lambda^{-10} + A_8 \lambda^{-12}$ with λ in μm
 2 Sellmeier Equation: $n^2 - 1 = B_1 \lambda^2 / (\lambda^2 - C_1) + B_2 \lambda^2 / (\lambda^2 - C_2) + B_3 \lambda^2 / (\lambda^2 - C_3) + B_4 \lambda^2 / (\lambda^2 - C_4)$ with λ in μm
 3 $\Delta n/\Delta T$ Equation: $\Delta n/\Delta T$ [ppm/K] = $C_0 + C_1 \lambda^{-2} + C_2 \lambda^{-4} + C_3 \lambda^{-6}$ with λ in μm

*We are here to help you specify the best product for your application.
For further information, please contact:*

Worldwide Accessibility

United States/Canada /Sales Office

Corning Incorporated
Semiconductor Optics Business
334 County Route 16
Canton, NY 13617

t: 315.379.3364
f: 315.379.3344
www.hpfs.corning.com

European Sales Office

Corning GmbH
Corning International
Abraham-Lincoln-Strasse 30
D-65189 Wiesbaden, Germany

t: 49.611.7366.100
f: 49.611.7366.143
e-mail: Cigermany@corning.com

Asia Sales Offices

Corning International K.K.
No. 35 Kowa Building, 3F
14-14, Akasaka 1-chome
Minato-Ku, Tokyo 107-0052
Japan

t: 81.3.3586.1052
f: 81.3.3587.0906

Corning International
1Kim Seng Promenade
#12-12
Great World City
West Tower
Singapore 237994
Republic of Singapore

t: 65.733.6511
f: 65.861.7310

Corning Korea Company Ltd.
10th Floor, Kukje Center Bldg.
191, Hangangro 2-Ka
Yongsan-Ku
Seoul, Korea 140-702

t: 82.2.796.9500
f: 82.2.796.9300

Corning Glass Taiwan Co. Ltd.
Room # 1023, 12F
No. 205
Tun Hua North Road Taipei,
Taiwan

t: 886.2.2716.0338
f: 886.2.2716.0339

Australia Sales Office

Corning International Australia
Suite 18
12, Tryon Road
Lindfield, NSW 2070
Australia

t: 61.2.9416.0492
f: 61.2.9416.0493

World Headquarters
Corning Incorporated
One Riverfront Plaza
Corning, NY 14831-0001

t: 607.974.9000

The information contained herein is based upon data considered to be accurate. However, no warranty is expressed or implied regarding the performance of this product. The only applicable warranties are those that are set out in a contract or purchase agreements.

Corning Incorporated

www.corning.com

Revision 21 January 2011
© Corning Incorporated 2011

**One Riverfront Plaza
Corning, NY 14831
t: 607.974.9000**

HPFS® is a registered trademark of Corning Incorporated